

C. L. Hauthaway & Sons Corporation
638 Summer Street Lynn, MA 01905-2092

781-592-6444
www.hauthaway.com
info@hauthaway.com

Chemical Spot Tests (1 Hour) – Ambient Temperature Cure

	HD-2007	HD-2015	HD-2101	HD-2107	HD-2113	HD-2209	HD-2314	HD-2139	HD-3011	HD-4664	HD-4669
Water	No Effect	No Effect	Softened	No Effect	Softened	No Effect	Softened	Softened	Hazy, Softened	Softened	Hazy, Softened
Toluene	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect
MEK	No Effect	Hazy	Slight Haze	No Effect	No Effect	No Effect	No Effect	No Effect	Very Slight Haze	No Effect	No Effect
IPA	No Effect	Hazy	No Effect	No Effect	Crazing	No Effect	No Effect	Crazing	No Effect	No Effect	No Effect
Ethanol	Hazy	Hazy	Sl. Haze	Hazy	Softened	Hazy	Softened	No Effect	No Effect	No Effect	No Effect
Fantastik	Softened	Softened	Softens	No Effect	No Effect	No Effect	Softened	Softened	Crazing	Hazy	Softened
Windex Non-drip	Softened	Softened	Softened	Softened	Crazing	Softened	Softened	Hazy	Softened	Softened	Softened
Acetic Acid 5%	No Effect	Softened	Softened	Softened	Softened	Softened	Softened	Slight Haze	Softened	Softened	Softened
Acetic Acid 20%	Slight Softening	Softened	Slight Softening	No Effect	Softened	Slight Softening	No Effect	No Effect	Softened	Slight Softening	Slight Softening
NaOH 20%	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect
NaOH 1N	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	Softened	Softened	Softened
Motor Oil	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect

Hauthaway

Established 1852

C. L. Hauthaway & Sons Corporation
638 Summer Street Lynn, MA 01905-2092

781-592-6444
www.hauthaway.com
info@hauthaway.com

Fedron (Cleaning solution - copiers)	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	No Effect	Crazing
--	-----------	-----------	-----------	-----------	-----------	-----------	-----------	-----------	-----------	-----------	-----------	---------

Coating film thickness: Applied at 4 mils wet on glass.

Curing schedule: 7 Days at Room Temperature