

C. L. Hauthaway & Sons Corporation
638 Summer Street Lynn, MA 01905-2092

781 592-6444
www.hauthaway.com

Hauthane L-2892

- DESCRIPTION:** An extremely hard, NMP-free, APEO-free, aliphatic, polyester-based, aqueous polyurethane dispersion with exceptional chemical and early water-resistance properties.
- SUGGESTED USES:** **L-2892** was designed for topcoat applications on a wide variety of substrates, including concrete, metal, plastic and wood. **L-2892** produces films with exceptional adhesion to aluminum, excellent leveling properties and high levels of chemical resistance.
- CHARACTERISTICS:** Contains dipropylene glycol dimethyl ether (DMM) co-solvent
Outstanding water and chemical resistance
Fast early water resistance development
Can be crosslinked to enhance performance
- APPLICATION:** **L-2892** can be used as a sole resin vehicle or blended with acrylic emulsions for spray or rotogravure applications. Rheology modifications can be made with associative thickeners for alternative application methods.
- DRYING:** **L-2892** may be dried at ambient temperatures with supplemental co-solvent addition of 5% DPM or DPnB on total formulation weight. Typical oven drying temperatures and dwell times for aqueous coatings are sufficient to produce optimal film properties without additional co-solvent.

PHYSICAL PROPERTIES

SOLIDS	35%(+/- 1%)
VISCOSITY	50-150 cps
pH	7.5-10.0
DENSITY	8.7 lbs/gal
SOFTENING POINT	350°F
VOC CONTENT	98 gm/l

TENSILE PROPERTIES

(TESTED AT 2 INCHES/MINUTE)	
ELONGATION	50%
TENSILE STRENGTH	>4850 psi
100% MODULUS	NA
200% MODULUS	NA
300% MODULUS	NA