

C. L. Hauthaway & Sons Corporation
638 Summer Street Lynn, MA 01905-2092

781 592-6444
www.hauthaway.com

Hauthane L-3790 (Experimental)

DESCRIPTION: A water-borne, UV-curable, polycarbonate-based polyurethane dispersion.

SUGGESTED USES: Hauthane **L-3790** is designed for UV-cured plastic topcoat applications where exterior weathering durability, abrasion-resistant and chemical-resistant films are required. Potential end-use applications include automotive plastics, kitchen cabinets and wood flooring.

CHARACTERISTICS:

- < Excellent chemical- and stain-resistance
- < Superior humidity resistance
- < Forms durable, films under ambient or force-dried conditions
- < APEO-free
- < Fast water-release properties
- < Contains dipropylene glycol dimethylether (DMM) co-solvent

APPLICATION: **L-3790** may be applied by spray or gravure methods. Films must be dried completely before UV energy cure. UV irradiation is required to attain optimal film properties, but un-cured coating films are durable enough for handling prior to curing.

CURING: **L-3790** must be air-dried, or oven dried (temperature: 150 – 170° F; dwell time: 10 minutes) to remove water from the film prior to UV exposure. A photo-initiator must be incorporated into the coating formulation for effective curing. See starting point formulations for suggestions. Exposure guidelines: MPMA lamp - 300 watts/in², 2.0 – 3.0 second dwell time.

PHYSICAL PROPERTIES

SOLIDS	35± 1%
VISCOSITY	50-500 cps
pH	7.5-10.0
DENSITY	8.8 lbs/gal
SOFTENING POINT	Uncured: 290°F Cured: >500°F
VOC CONTENT	75 g/l (as supplied) 192 g/l (less water)
SWARD HARDNESS	After UV-curing - 64